

# REPORT No 11288

*Date of issue: August 8, 2025*

**Status: FINAL REPORT**

\*\*\*\*\*

## ISO 3795

# DETERMINATION OF BURNING BEHAVIOUR OF INTERIOR MATERIALS

## Program: SQO-PL3 Round 10

\*\*\*\*\*

This document is issued by the Company subject to its Terms and Conditions, available on request or accessible at <https://www.ptsouthquality.com/terms-and-conditions>. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Copyright © 2024 South Quality, Buenos Aires, ARGENTINA



<b>Prepared by:</b>	<b>Reviewed by:</b>	<b>Approved by:</b>
<b>Berenice Ferrel</b> Assistant Technician	<b>Lic. Esther Casas</b> Physics expert	<b>Eng. Emiliano Medina</b> Quality Assurance Lead

# TABLE OF CONTENTS

<b>1. FOREWORD</b>	<b>3</b>
<b>2. ORGANIZATION</b>	<b>3</b>
<b>3. OBJECTIVE</b>	<b>3</b>
<b>4. PARTICIPANTS</b>	<b>4</b>
<b>5. HOMOGENEITY</b>	<b>5</b>
<b>6. SAMPLE INFORMATION</b>	<b>5</b>
<b>7. IMAGES</b>	<b>6</b>
<b>8. ASSIGNED VALUES</b>	<b>6</b>
<b>9. PARTICIPANT RESULTS</b>	<b>7</b>
<b>10. STATISTICS</b>	<b>8</b>
<b>11. EVALUATION OF PERFORMANCE</b>	<b>9</b>
<b>12. CONCLUSIONS</b>	<b>12</b>
<b>APPENDIX A</b>	
<b>A1 - PARTICIPANT DATA</b>	<b>13</b>
<b>A2 - PARTICIPANT RESULTS</b>	<b>13</b>
<b>APPENDIX B</b>	<b>17</b>

## 1. FOREWORD

This report summarizes the results of the **SQO-PL13 Round 10** proficiency testing program on the determination of horizontal burning of interior materials. This program is carried out under a simultaneous participation format, according to the A.3.1 classification of the ISO 17043 standard (“Model 2 - Figure A.1”).

**South Quality** conducted the testing program in June/July 2025. The aim of the program was to assess laboratory ability to competently perform the nominated tests.

## 2. ORGANIZATION

Program Coordinator: Lic. Esther Casas  
 Assistant Technician: Berenice Ferrel  
 Statistic: Lic. Manuel Tozaki  
 Supervision: Eng. Emiliano Medina

## 3. OBJECTIVE

The objective of this proficiency testing program is to determine the burning rates of materials. This parameter is verified using the following standard:

Standard
ISO 3795: 1989

For the verification of this, thermoplastic samples have been selected.

Participants in this program have not been previously informed of the values or range of values expected from the samples they receive.

#### 4. PARTICIPANTS

In the present round, 20 laboratories have participated with the following details:

CODE	Country	ISO 17025 Accredited	Results delivered
01	Colombia	Yes	Yes
02	South Africa	Yes	Yes
03	Chile	No	Yes
04	Hong Kong	Yes	Yes
05	Canada	Yes	Yes
06	Malaysia	Yes	Yes
07	Netherlands	Yes	Yes
08	Mexico	Yes	No
09	Australia	Yes	Yes
10	Germany	Yes	Yes
11	France	No	Yes
12	Peru	No	Yes
13	Spain	Yes	Yes
14	Italy	Yes	Yes
15	Brazil	Yes	Yes
16	France	Yes	Yes
17	Spain	Yes	Yes
18	Portugal	Yes	Yes
19	Türkiye	Yes	Yes
20	Brazil	Yes	Yes

## 5. HOMOGENEITY

Several batches were prepared by South Quality personnel in an identical way.

Then, a homogeneity study was then carried out with an ISO 17025 accredited laboratory.

Control was carried out according to ISO Guide 35: 2017, clause 7.4.1.2. Stratified random sampling was applied. Samples were selected using random number generation software.

The results of this test appear below:

Size of each batch: **50 samples**

Tested samples from each batch: **15 samples**

DETERMINATION	HOMOGENEITY OF RESULTS IN THE ANALYZED SAMPLES		
	BATCH: LP2407	BATCH: LP2408	BATCH: LP2409
BURNING RATE	YES	YES	YES

Size of each batch: **50 samples**

Tested samples from each batch: **15 samples**

DETERMINATION	HOMOGENEITY OF RESULTS IN THE ANALYZED SAMPLES		
	BATCH: LP2674	BATCH: LP2675	BATCH: LP2676
BURNING RATE	NO	YES	YES

Samples for this program are taken from selected batches identified as LP2408, and LP2675.

The analysis of the test data indicated that the selected samples exhibited sufficient homogeneity for the program. Therefore, the results of participants identified as outliers cannot be attributed to sample variability.

## 6. SAMPLE INFORMATION

The following samples were sent for testing (Participant **Code 15**):

Batch:	LP2408
Sample ID:	15
Characteristics:	Black thermoplastic - 360 x 110 x 0.9 mm - 5 units

Batch:	L2675
Sample ID:	15
Characteristics:	Grey thermoplastic - 360 x 110 x 0.9 mm - 5 units

## 7. IMAGES



## 8. ASSIGNED VALUES

The assigned values are obtained from the results reported by all participants (**Consensus values**).

## 9. PARTICIPANT RESULTS

LABORATORY CODE	BURNING RATE - AVG (mm/s)	
	BATCH: LP2408	BATCH: LP2675
01	0.65	0.95
02	2.76	2.08
03	1.49	1.67
04	2.32	2.01
05	2.05	1.99
06	2.10	2.25
07	1.57	1.70
09	1.60	1.49
10	2.10	1.88
11	2.20	1.96
12	2.45	2.86
13	1.33	1.24
14	3.30	2.90
15	1.82	1.47
16	2.17	1.80
17	2.53	1.83
18	1.16	1.08
19	2.45	1.67
20	1.24	1.09

ASSIGNED VALUES - BURNING RATE (mm/s)			
LEM2419		LEM3225	
AVG	SD	AVG	SD
1.96	0.64	1.79	0.53

## 10. STATISTICS

The results must be treated as quantitative.

According B.3.1.3 of ISO 17043 the appropriate technique is to compare participant results with the assigned values. The results can be compare using **z score**.

$$z = \frac{x - X}{\hat{\sigma}}$$

$x$  is the participant's result

$X$  is the assigned value

$\hat{\sigma}$  is the standard deviation

The performance evaluation of each sample is carried out with the following criteria:

**$|z| \leq 2.0$  indicates “satisfactory” performance and generates no signal;**

**$2.0 < |z| < 3.0$  indicates “questionable” performance and generates a warning signal;**

**$|z| \geq 3.0$  indicates “unsatisfactory” performance and generates an action signal;**

## 11. EVALUATION OF PERFORMANCE

LABORATORY CODE	z score	
	BATCH: LP2408	BATCH: LP2675
01	2.05	1.58
02	1.25	0.55
03	0.73	0.23
04	0.56	0.42
05	0.14	0.38
06	0.22	0.87
07	0.61	0.17
09	0.56	0.57
10	0.22	0.17
11	0.38	0.32
12	0.77	2.02
13	0.98	1.04
14	2.09	2.09
15	0.22	0.60
16	0.33	0.02
17	0.89	0.08
18	1.25	1.34
19	0.77	0.23
20	1.13	1.32

Laboratory Code 01: The laboratory obtained a **QUESTIONABLE** result for the LP2408 samples. Additionally, **SATISFACTORY** results were obtained for LP2675 samples.

Laboratory Code 02: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 03: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 04: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 05: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 06: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 07: The laboratory has not sent the results before the deadline.

Laboratory Code 08: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 09: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 10: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 11: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 12: The laboratory obtained a **QUESTIONABLE** result for the LP2675 samples. Additionally, **SATISFACTORY** results were obtained for LP2408 samples.

Laboratory Code 13: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 14: The laboratory has obtained **QUESTIONABLE** results for both samples.

Laboratory Code 15: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 16: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 17: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 18: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 19: The laboratory obtained **SATISFACTORY** results for both samples.

Laboratory Code 20: The laboratory obtained **SATISFACTORY** results for both samples.

## GLOBAL PERFORMANCE - SUM OF ABSOLUTE Z SCORE

POSITION	LABORATORY CODE	Z SCORE
1 <sup>st</sup>	16	0.35
2 <sup>nd</sup>	10	0.39
3 <sup>rd</sup>	05	0.52
4 <sup>th</sup>	11	0.70
5 <sup>th</sup>	07	0.78
6 <sup>th</sup>	15	0.82
7 <sup>th</sup>	03	0.96
8 <sup>th</sup>	17	0.97
9 <sup>th</sup>	04	0.98
10 <sup>th</sup>	19	1.00
11 <sup>th</sup>	06	1.09
12 <sup>th</sup>	09	1.13
13 <sup>th</sup>	02	1.80
14 <sup>th</sup>	13	2.02
15 <sup>th</sup>	20	2.45
16 <sup>th</sup>	18	2.59
17 <sup>th</sup>	12	2.79
18 <sup>th</sup>	01	3.63
19 <sup>th</sup>	14	4.18

## 12. CONCLUSIONS

The overall performance on this **SQO-PL13 Round 10** program from the participating laboratories, based on expected results, are the following:

- Laboratories Codes **02, 03, 04, 05, 06, 07, 09, 10, 11, 13, 15, 16, 17, 18, 19** and **20** have obtained a **SUFFICIENT** performance according to the expected results and should not take action;
- Laboratories Codes **01**, and **12** have obtained an **ALMOST SUFFICIENT** performance according to the expected results and must evaluate if it is necessary to take corrective action.
- Laboratory Code **14** has obtained an **INSUFFICIENT** performance in accordance with the expected results and must take corrective action.

The criteria used for the evaluation of the overall performance is the following:


- **SUFFICIENT** performance: No unsatisfactory/questionable results obtained.
- **ALMOST SUFFICIENT** performance: No unsatisfactory results were obtained, but one questionable result was found.
- **INSUFFICIENT** performance: An unsatisfactory result or two questionable results were obtained.

## APPENDIX A

### A1 - PARTICIPANT DATA

Company: **ITEN - Instituto Tecnológico de Ensaios Ltda**  
Country: Brazil  
Client ID: C080  
Contact person: Renata Vieira  
( [qualidade@itensp.com.br](mailto:qualidade@itensp.com.br) )

### A2 - PARTICIPANT RESULTS



 **SOUTH  
QUALITY**  
PROFICIENCY TESTING PROVIDER

# INSTRUCTIONS & RESULTS FORM

<b>PROGRAM:</b>	Determination of burning behaviour of interior materials
<b>CODE:</b>	SQO-PL13
<b>ROUND:</b>	10
<b>STANDARD:</b>	ISO 3795
<b>COORDINATOR:</b>	Lic. Esther Casas ( <a href="mailto:ecasas@ptsouthquality.com">ecasas@ptsouthquality.com</a> )

DSQ-012 - REV 05 - SQO-PL13 R10 May 2025 1 de 4

### 1 - General

This document is intended to be filled with the results of the **SQO-PL13** program, round 10.

Results must be typed, not handwritten.

### 2 - Standard

**ISO 3795: 1989**

### 3 - Participant

ITEN - Instituto Tecnológico de Ensaio Ltda	CODE 15
---	---------

### 4 - Tests involved

TEST
Determination the horizontal burning rate of materials

### 5 - Samples

CODE	SAMPLE	QUANTITY
LP2408-XX	Black thermoplastic - 360 x 110 x 0.9 mm	5
LP2675-XX	Grey thermoplastic - 360 x 110 x 1 mm	5

### 6 - Notes

- a) The deadline for the delivery of results is **July 9, 2025**.
- b) The tables in this document may be modified by the participant, if desired, to include data or observations.
- c) The samples must be oriented such that the outer surface of the material's curvature is positioned upward.
- d) The samples must be kept until the end of the program, which closes with the submission of the final report.
- e) To review the results, the submission of images of the tests is appreciated. These images can be attached at the end of this document or sent via email.
- f) Upon completion of this document, please convert it to a PDF file and send it to the program coordinator.

## 7 - Test results

Test date:	17/07/2025
------------	------------

CONDITIONING		TESTING ENVIROMENT	
Temperature (°C):	23,2°C	Max. temperature (°C):	23,8°C
Relative humidity (%):	52%	Min. temperature (°C):	23,2°C
Time (h):	24h	Max. relative humidity (%):	54%
		Min. relative humidity (%):	51%

SAMPLE	Burnt distance (mm)	Burning time (s)	Burning rate (mm/s)	Observations	
LP2408-15	I	254	126	2,02	COMPLETELY CARBONIZED
	II	147	85	1,73	-
	III	160	96	1,67	-
	IV	254	131	1,94	COMPLETELY CARBONIZED
	V	182	106	1,72	-

SAMPLE	Burnt distance (mm)	Burning time (s)	Burning rate (mm/s)	Observations	
LP2675-15	I	160	122	1,31	-
	II	254	147	1,73	COMPLETELY CARBONIZED
	III	254	200	1,27	COMPLETELY CARBONIZED
	IV	254	153	1,66	COMPLETELY CARBONIZED
	V	186	133	1,4	-

OBSERVATIONS				

**PHOTOGRAPHS**



**LP2408-15 – SAMPLE BEFORE**



**LP2675-15 – SAMPLE BEFORE**



**LP2408-15 – SAMPLE AFTER**



**LP2676-16 – SAMPLE AFTER**

# APPENDIX B

**VOID**

**----- END OF REPORT -----**