

REPORT No 11291

Date of issue: August 15, 2025

Status: FINAL REPORT

NACE TM 0284

EVALUATION OF PIPELINE AND PRESSURE VESSEL STEELS FOR RESISTANCE TO HYDROGEN-INDUCED CRACKING

Program: SQO-M4 Round 17

This document is issued by the Company subject to its Terms and Conditions, available on request or accessible at <https://www.ptsouthquality.com/terms-and-conditions>. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Copyright © 2024 South Quality, Buenos Aires, ARGENTINA



Prepared by:	Reviewed by:	Approved by:
Sergio Andrada Assistant Technician	Eng. Alfredo Schmidt Metallurgical expert	Eng. Emiliano Medina Quality Assurance Lead

TABLE OF CONTENTS

1. FOREWORD	3
2. ORGANIZATION	3
3. OBJECTIVE	3
4. PARTICIPANTS	4
5. HOMOGENEITY	5
6. SAMPLE INFORMATION	6
7. IMAGES	6
8. ASSIGNED VALUES	6
9. PARTICIPANTS' RESULTS	7
10. STATISTICS	8
11. EVALUATION OF PERFORMANCE	9
12. CONCLUSIONS	11
APPENDIX A	
A1 - PARTICIPANT DATA	12
A2 - PARTICIPANT RESULTS	12
A3 - TEST PROTOCOL (EDWK2025-047)	15
A4 - TEST PROTOCOL (EDWK2025-048)	18
APPENDIX B	18

1. FOREWORD

This report summarizes the results of the **SQO-M4 (Round 17)** proficiency testing program on the evaluation of the resistance of pressure vessel plate steels to HIC caused by hydrogen absorption from aqueous sulfide corrosion. This program is carried out under a simultaneous participation format, according to the A.3.1 classification of the ISO 17043 standard (“Model 2 - Figure A.1”).

South Quality conducted the testing program between June and August 2025. The aim of the program was to assess laboratory ability to competently perform the nominated tests.

2. ORGANIZATION

Program Coordinator:	Eng. Alfredo Schmidt
Assistant Technician:	Sergio Andrada
Statistic:	Lic. Manuel Tozaki
Supervision:	Eng. Emiliano Medina

3. OBJECTIVE

The objective of this proficiency testing program is to evaluate the resistance of pressure vessel plate steels to HIC caused by hydrogen absorption from aqueous sulfide corrosion, using the following standard:

Standard
ANSI/NACE TM0284: 2016

Batches of steels samples have been selected.

Participants in this program have not been previously informed of the values or the expected range of values for the samples they will receive.

4. PARTICIPANTS

In the present round, 22 laboratories have participated with the following details:

CODE	Country	ISO 17025 Accredited	Results delivered
01	Brazil	Yes	Yes
02	Malaysia	Yes	Yes
03	France	Yes	No
04	Spain	No	Yes
05	Peru	No	Yes
06	Brazil	Yes	Yes
07	Spain	Yes	No
08	Portugal	Yes	Yes
09	Spain	Yes	Yes
10	Pakistan	No	Yes
11	Italy	Yes	Yes
12	Mexico	Yes	Yes
13	Türkiye	Yes	Yes
14	Argentina	Yes	No
15	Colombia	Yes	Yes
16	Australia	Yes	Yes
17	Germany	Yes	Yes
18	England	Yes	Yes
19	Romania	Yes	Yes
20	Hong Kong	Yes	No
21	Germany	Yes	Yes
22	France	No	Yes

5. HOMOGENEITY

Several batches were prepared identically by South Quality staff.

Subsequently, a homogeneity study was conducted with an ISO 17025 accredited laboratory.

The control process followed ISO Guide 35: 2017, clause 7.4.1.2. Stratified random sampling was employed, and samples were chosen using random number generation software.

The results of these tests are presented below:

Size of each batch: **150 samples**

Tested samples from each batch: **30 samples**

DETERMINATION (SOLUTION A)	HOMOGENEITY OF RESULTS IN THE ANALYZED SAMPLES - LOW CARBON STEEL -		
	BATCH: LM3419	BATCH: LM3420	BATCH: LM3421
CSR	YES	YES	YES
CLR	YES	YES	YES
CTR	YES	YES	YES

Size of each batch: **150 samples**

Tested samples from each batch: **30 samples**

DETERMINATION (SOLUTION B)	HOMOGENEITY OF RESULTS IN THE ANALYZED SAMPLES - STAINLESS STEEL -		
	BATCH: LM3442	BATCH: LM3528	BATCH: LM3529
CSR	NO	NO	YES
CLR	NO	NO	YES
CTR	NO	NO	YES

Samples for this program are taken from selected batches identified as **LM3421** and **LM3528**.

Analysis of this testing data indicated that samples were sufficiently homogeneous for the program and, therefore, any participant results identified as outliers cannot be attributed to sample variability.

6. SAMPLE INFORMATION

The following samples were sent for testing (Participant **Code 21**):

Batch:	LM3421
Sample ID:	42 + 88 + 129
Characteristics:	Carbon steel (SAE 1010) - 100 x 19.1 x 9.5 mm

Batch:	LM3528
Sample ID:	33 + 78 + 134
Characteristics:	Stainless steel (AISI 304) - 100 x 19.1 x 9.5 mm

7. IMAGES



8. ASSIGNED VALUES

The assigned values are obtained from the results reported by all participants (**Consensus values**).

9. PARTICIPANTS' RESULTS

LABORATORY CODE	LM3421			LM3528		
	MEAN			MEAN		
	CSR	CLR	CTR	CSR	CLR	CTR
01	0.250	2.591	5.448	0	0	0
02	0.117	4.247	3.516	0	0	0
04	1.131	4.112	3.275	0	0	0
05	1.389	2.335	9.523	0	0	0
06	0.336	4.001	5.207	0	0	0
08	1.445	2.014	3.161	0	0	0
09	0.659	2.591	2.866	0	0	0
10	0.781	5.953	2.636	0	0	0
11	0.488	2.719	2.225	0	0	0
12	0.913	6.859	3.123	0	0.05	0.04
13	1.051	2.847	2.495	0	0	0
15	1.378	4.045	3.874	0	0	0
16	1.168	1.472	2.886	0	0	0
17	1.680	4.600	6.220	0	0.03	0.09
18	1.304	1.640	5.442	0	0	0
19	0.398	0.654	0.007	0	0	0
21	0.420	4.470	6.950	0	0	0
22	1.472	1.632	4.915	0	0	0

ASSIGNED VALUES				
PARAMETER	LM3421		LM3528	
	AVG	SD	AVG	SD
CSR	0.910	0.490	0	-
CLR	3.054	1.407	0	-
CTR	4.098	2.148	0	-

10. STATISTICS

The results must be treated as qualitative as quantitative.

According B.3.1.3 of ISO 17043 the appropriate technique is to compare participant results with the assigned values.

- a) For qualitative results (Values equal to zero), the comparison will be made directly against the assigned value, and any difference will be evaluated as **Unsatisfactory**.
- b) For quantitative results the comparison will be made through z **score** (B3 - ISO 17043).

$$z = \frac{x - X}{\hat{\sigma}}$$

x is the participant's result

X is the assigned value

$\hat{\sigma}$ is the standard deviation

The performance evaluation of each sample is carried out with the following criteria:

$|z| \leq 2.0$ indicates “satisfactory” performance and generates no signal;

$2.0 < |z| < 3.0$ indicates “questionable” performance and generates a warning signal;

$|z| \geq 3.0$ indicates “unsatisfactory” performance and generates an action signal;

11. EVALUATION OF PERFORMANCE

LABORATORY CODE	z score - BATCH: LM3421		
	CSR	CLR	CTR
01	1.35	0.33	0.63
02	1.62	0.85	0.27
04	0.45	0.75	0.38
05	0.98	0.51	2.53
06	1.17	0.67	0.52
08	1.09	0.74	0.44
09	0.51	0.33	0.57
10	0.26	2.06	0.68
11	0.86	0.24	0.87
12	0.20	3.36	0.26
13	0.29	0.15	0.75
15	0.96	0.70	0.10
16	0.53	1.12	0.56
17	1.88	1.55	1.41
18	0.80	1.00	0.63
19	0.92	1.59	1.95
21	0.88	1.45	1.80
22	1.15	1.01	0.38

Laboratory **Code 01**: The laboratory obtained **SATISFACTORY** results for the determination of all assigned values in both samples.

Laboratory **Code 02**: The laboratory obtained **SATISFACTORY** results for the determination of all assigned values in both samples.

Laboratory Code 03: The laboratory has not sent the results before the deadline.

Laboratory Code 04: The laboratory obtained **SATISFACTORY** results for the determination of all assigned values in both samples.

Laboratory Code 05: The laboratory obtained **QUESTIONABLE** results for the CTR parameter determination in the sample from batch LM3421. However, **SATISFACTORY** results were achieved for all other parameters in both samples.

Laboratory Code 06: The laboratory obtained **SATISFACTORY** results for the determination of all assigned values in both samples.

Laboratory Code 07: The laboratory has not sent the results before the deadline.

Laboratory Code 08: The laboratory obtained **SATISFACTORY** results for the determination of all assigned values in both samples.

Laboratory Code 09: The laboratory obtained **SATISFACTORY** results for the determination of all assigned values in both samples.

Laboratory Code 10: The laboratory obtained **QUESTIONABLE** results for the CLR parameter determination in the sample from batch LM3421. However, **SATISFACTORY** results were achieved for all other parameters in both samples.

Laboratory Code 11: The laboratory obtained **SATISFACTORY** results for the determination of all assigned values in both samples.

Laboratory Code 12: The laboratory obtained **UNSATISFACTORY** results for the CLR parameter determination in the sample from batch LM3421 and for the CLR and CTR parameters in the sample from batch LM3528. However, **SATISFACTORY** results were achieved for all other parameters in both samples.

Laboratory Code 13: The laboratory obtained **SATISFACTORY** results for the determination of all assigned values in both samples.

Laboratory Code 14: The laboratory has not sent the results before the deadline.

Laboratory Code 15: The laboratory obtained **SATISFACTORY** results for the determination of all assigned values in both samples.

Laboratory Code 16: The laboratory obtained **SATISFACTORY** results for the determination of all assigned values in both samples.

Laboratory Code 17: The laboratory obtained **UNSATISFACTORY** results for the CLR and CTR parameters in the sample from batch LM3528. However, **SATISFACTORY** results were achieved for all other parameters in both samples.

Laboratory Code 18: The laboratory obtained **SATISFACTORY** results for the determination of all assigned values in both samples.

Laboratory Code 19: The laboratory obtained **SATISFACTORY** results for the determination of all assigned values in both samples.

Laboratory Code 20: The laboratory has not sent the results before the deadline.

Laboratory Code 21: The laboratory obtained **SATISFACTORY** results for the determination of all assigned values in both samples.

Laboratory Code 22: The laboratory obtained **SATISFACTORY** results for the determination of all assigned values in both samples.

12. CONCLUSIONS

The overall performance of participating laboratories in the **SQO-M4 (Round 17)** program, based on expected results, is summarized as follows:

- Laboratories Codes **01, 02, 04, 06, 08, 09, 11, 13, 15, 16, 18, 19, 21, and 22** have obtained a **SUFFICIENT** performance according to the expected results and should not take any action;
- Laboratories Codes **05, and 10** has obtained an **ALMOST SUFFICIENT** performance according to the expected results and must evaluate whether it is necessary to take action on the tests where they obtained a different result than expected;
- Laboratory Code **12, and 17** has obtained an **INSUFFICIENT** performance according to the expected results and must take action on the tests where they obtained a different result than expected (See Appendix B).

The criteria used for evaluating overall performance are as follows:

- **SUFFICIENT** performance: No unsatisfactory or questionable results were obtained.
- **ALMOST SUFFICIENT** performance: No unsatisfactory results were obtained, but one questionable result was found.
- **INSUFFICIENT** performance: One unsatisfactory result or two questionable results were obtained.

APPENDIX A

A1 - PARTICIPANT DATA

Company: **SALZGITTER MANNESMANN FORSCHUNG GMBH**

Laboratory: EDWK Corrosion

City-Country: Duisburg - Germany

Client ID: E529

Contact person: Dr. Thomas Haase - Specialist Corrosion
t.haase@du.szmf.de

A2 - PARTICIPANT RESULTS


**SOUTH
QUALITY**
 PROFICIENCY TESTING PROVIDER

INSTRUCTIONS & RESULTS FORM

PROGRAM:	Evaluation of pipeline and pressure vessel steels for resistance to hydrogen-induced cracking
CODE:	SQO-M4
ROUND:	17
STANDARD:	NACE TM 0284
COORDINATOR:	Eng. Alfredo Schmidt (aschmidt@ptsouthquality.com)

DSQ-015 - REV 04 -
SQO-M4 R17
May 2025
1 of 5

1 - General

This document is intended to be filled with the results of the **SQO-M4** program (Round 17).

Results must be typed, not handwritten.

2 - Standard

ANSI/NACE TM0284: 2016

3 - Participant

<p style="text-align: center;">SALZGITTER MANNESMANN FORSCHUNG GMBH EDWK Corrosion - Duisburg</p>	<p style="text-align: center;">CODE 21</p>
--	---

4 - Tests involved

TEST
Evaluation of the resistance of pressure vessel plate steels to HIC caused by hydrogen absorption from aqueous sulfide corrosion

5 - Samples

CODE	SAMPLE	QUANTITY
LM3421-XX	Steel - 100 x 19.1 x 9.5 mm	3
LM3528-XX	Steel - 100 x 19.1 x 9.5 mm	3

6 - Notes

- a) The deadline for the delivery of results is **July 21, 2025**.
- b) Tables in this document may be modified to include additional data or observations.
- c) Samples must be retained until the end of the program, which concludes with the submission of the final report.
- d) Participants may improve the surface to ensure a better testing area. If so, the procedure must be described in the observations box.
- e) Samples **LM3421** are to be tested using **solution A**.
- f) Samples **LM3528** are to be tested using **solution B**.
- g) The sample should be treated as a routine laboratory specimen. All testing, recording, and reporting must be carried out in accordance with ANSI/NACE TM0284.
- h) To support the review of results, submission of test images is appreciated. Images may be attached at the end of this document or sent via email.
- i) Once the document is completed, please convert it to a PDF file and send it to the program coordinator.

7 - Test results

Test date:	27.06.2025 – 01.07.2025	Solution:	A
Sample preparation:	Grinding <input checked="" type="checkbox"/>	Test duration:	96 h
	Sawing <input type="checkbox"/>	pH at start of test:	2,9
	Machining <input type="checkbox"/>	pH at end of test:	3,8
Polished grade:	320 grit	Solution temperature:	25 °C
Method of testing of adequacy degreasing:	ASTM F21	H ₂ S concentration (mg/L):	2844 (start) / 2980 (end)
		Purged inert gas:	Nitrogen 5.0

SAMPLE	DIMENSIONS (mm)		
	LENGTH	WIDE	THICKNESS
LM3421-42	100,8	17,9	8,8
LM3421-88	100,4	17,9	8,8
LM3421-129	100,7	17,9	8,8

SAMPLE	SECTION	RESULTS (%)		
		CSR	CLR	CTR
LM3421-42	I	1,23	8,88	13,86
	II	0,00	0,00	0,00
	III	1,27	11,17	27,61
LM3421-88	I	0,34	9,22	6,02
	II	0,03	1,62	1,93
	III	0,83	7,32	11,36
LM3421-129	I	0,00	0,00	0,00
	II	0,03	2,01	1,70
	III	0,00	0,00	0,00
MEAN		0,42	4,47	6,95

OBSERVATIONS
Specimens surfaces were reworked by using grinding paper (320 grit).


Test date:	27.06.2025 – 01.07.2025	Solution:	B
Sample preparation:	Grinding <input checked="" type="checkbox"/>	Test duration:	96 h
	Sawing <input type="checkbox"/>	pH at start of test:	5,1
	Machining <input type="checkbox"/>	pH at end of test:	5,2
Polished grade:	320 grit	Solution temperature:	25 °C
Method of testing of adequacy degreasing:	ASTM F21	H ₂ S concentration (mg/L):	2827 (start) / 2793 (end)
		Purged inert gas:	Nitrogen 5.0

SAMPLE	DIMENSIONS (mm)		
	LENGTH	WIDE	THICKNESS
LM3528-33	100,5	18,0	9,2
LM3528-78	100,8	18,0	9,2
LM3528-134	100,2	18,0	8,8

SAMPLE	SECTION	RESULTS (%)		
		CSR	CLR	CTR
LM3528-33	I	0,00	0,00	0,00
	II	0,00	0,00	0,00
	III	0,00	0,00	0,00
LM3528-78	I	0,00	0,00	0,00
	II	0,00	0,00	0,00
	III	0,00	0,00	0,00
LM3528-134	I	0,00	0,00	0,00
	II	0,00	0,00	0,00
	III	0,00	0,00	0,00
MEAN		0,00	0,00	0,00



OBSERVATIONS
Specimens surfaces were reworked by using grinding paper (320 grit).

PHOTOGRAPHS



A3 - TEST PROTOCOL (EDWK2025-047)



Customer		TEST PROTOCOL						Order no.		
South Quality		(Hydrogen Induced Cracking Test - HIC)						SQO-M4 R17		
Plate - no. ^a		Material ^a			Heat - no. ^a			Dimensions [mm] ^a		
		Steel								
Tube - no. ^a		Specimen - no. ^a		Specimen size [mm] ^b			Work-no.			
LM3421		42		Width	Thickness	Length	EDWK2025-047			
				17,9	8,8	100,8				
Specification		NACE Standard TM0284-2016								
	Specimen location	Specimen 1	x	Longitudinal specimen	Specimen 1	x	Transverse specimen	Specimen 1		
		Specimen 2			Specimen 2			Specimen 2		
		Specimen 3			Specimen 3			Specimen 3		
		Specimen 4			Specimen 4			Specimen 4		
O2 concentration										
Purge gas		Nitrogen 5.0								
Test solution		NACE Standard TM0284-2016 test solution A								
Test conditions		Temperature 25 °C		Test period 96 h						
		before H ₂ S	Test start	Day 1	Day 2	Day 3	Test end			
pH		2,7	2,9				3,8			
H ₂ S concentration (ppm)			2844				2980			
Subsection A			Subsection B			Subsection C				
L [mm]	W [mm]	A [mm ²]	L [mm]	W [mm]	A [mm ²]	L [mm]	W [mm]	A [mm ²]		
1,59	1,22	1,940				0,21	0,09	0,019		
						0,96	0,35	0,336		
						0,83	1,99	1,652		
CLR %	CTR %	CSR %	CLR %	CTR %	CSR %	CLR %	CTR %	CSR %		
8,88	13,86	1,23	0,00	0,00	0,00	11,17	27,61	1,27		
average over 3 subsections		CLR = 6,69 %		CTR = 13,83 %		CSR = 0,84 %				
Corrosion laboratory		Metallography			Inspector					
Received on		27.06.2025								
Completed on		01.07.2025			14.07.2025					
Operator		Boenke			Förster					
Signature										
Approved on		14.07.2025								
Name		Dr. Haase								
Signature										



Test results only refer to the pieces tested. No part of this protocol may be reproduced without prior written permission of SZMF.

Salzgitter Mannesmann Forschung GmbH, Standort Duisburg - Ehinger Straße 200, 47259 Duisburg - Phone: 0203 / 999 - 02

^aCustomer information (Kunden-/Auftraggeberinformationen)

^bSampling by customer (Probenentnahme kundenseitig)



Customer		TEST PROTOCOL						Order no.		
South Quality		(Hydrogen Induced Cracking Test - HIC)						SQO-M4 R17		
Plate - no. ^a		Material ^a			Heat - no. ^a			Dimensions [mm] ^a		
		Steel								
Tube - no. ^a		Specimen - no. ^a		Specimen size [mm] ^b			Work-no.			
LM3421		129		Width	Thickness	Length	EDWK2025-047			
				17,9	8,8	100,7				
Specification		NACE Standard TM0284-2016								
	Specimen location	Specimen 1	x	Longitudinal specimen	Specimen 1	x	Transverse specimen	Specimen 1		
		Specimen 2			Specimen 2			Specimen 2		
		Specimen 3			Specimen 3			Specimen 3		
		Specimen 4			Specimen 4			Specimen 4		
O2 concentration										
Purge gas		Nitrogen 5.0								
Test solution		NACE Standard TM0284-2016 test solution A								
Test conditions		Temperature 25 °C			Test period 96 h					
		before H ₂ S	Test start	Day 1	Day 2	Day 3	Test end			
pH		2,7	2,9				3,8			
H ₂ S concentration (ppm)			2844				2980			
Subsection A			Subsection B			Subsection C				
L [mm]	W [mm]	A [mm ²]	L [mm]	W [mm]	A [mm ²]	L [mm]	W [mm]	A [mm ²]		
			0,36	0,15	0,054					
CLR %	CTR %	CSR %	CLR %	CTR %	CSR %	CLR %	CTR %	CSR %		
0,00	0,00	0,00	2,01	1,70	0,03	0,00	0,00	0,00		
average over 3 subsections			CLR =	0,67 %						
			CTR =	0,57 %						
			CSR =	0,01 %						
		Corrosion laboratory	Metallography		Inspector					
Received on		27.06.2025								
Completed on		01.07.2025	14.07.2025							
Operator		Boenke	Förster							
Signature										
Approved on		14.07.2025								
Name		Dr. Haase								
Signature										

Test results only refer to the pieces tested. No part of this protocol may be reproduced without prior written permission of SZMF.
 Salzgitter Mannesmann Forschung GmbH, Standort Duisburg - Ehinger Straße 200, 47259 Duisburg - Phone: 0203 / 999 - 02


^aCustomer information (Kunden-/Auftraggeberinformationen)

Page 3 of 3

^bSampling by customer (Probenentnahme kundenseitig)

A4 - TEST PROTOCOL (EDWK2025-048)



Customer		TEST PROTOCOL						Order no.		
South Quality		(Hydrogen Induced Cracking Test - HIC)						SQO-M4 R17		
Plate - no. ^a		Material ^a			Heat - no. ^a			Dimensions [mm] ^a		
		Steel								
Tube - no. ^a		Specimen - no. ^a		Specimen size [mm] ^b			Work-no.			
LM3528		33		Width	Thickness	Length	EDWK2025-048			
				18,0	9,2	100,5				
Specification		NACE Standard TM0284-2016								
	Specimen location	Specimen 1	x	Longitudinal specimen	Specimen 1	x	Transverse specimen	Specimen 1		
		Specimen 2			Specimen 2			Specimen 2		
		Specimen 3			Specimen 3			Specimen 3		
		Specimen 4			Specimen 4			Specimen 4		
O ₂ concentration										
Purge gas		Nitrogen 5.0								
Test solution		NACE Standard TM0284-2016 test solution B								
Test conditions		Temperature 25 °C			Test period 96 h					
		before H ₂ S	Test start	Day 1	Day 2	Day 3	Test end			
pH		8,2	5,1				5,2			
H ₂ S concentration (ppm)			2827				2793			
Subsection A			Subsection B			Subsection C				
L [mm]	W [mm]	A [mm ²]	L [mm]	W [mm]	A [mm ²]	L [mm]	W [mm]	A [mm ²]		
CLR %	CTR %	CSR %	CLR %	CTR %	CSR %	CLR %	CTR %	CSR %		
0,00	0,00	0,00	0,00	0,00	0,00	0,00	0,00	0,00		
average over 3 subsections		CLR =	0,00 %							
		CTR =	0,00 %							
		CSR =	0,00 %							
		Corrosion laboratory		Metallography		Inspector				
Received on		27.06.2025								
Completed on		01.07.2025		14.07.2025						
Operator		Boenke		Förster						
Signature										
Approved on		14.07.2025								
Name		Dr. Haase								
Signature										



*Test results only refer to the pieces tested. No part of this protocol may be reproduced without prior written permission of SZMF.

Salzgitter Mannesmann Forschung GmbH, Standort Duisburg - Ehinger Straße 200, 47259 Duisburg - Phone: 0203 / 999 - 02

^aCustomer information (Kunden-/Auftraggeberinformationen)

^bSampling by customer (Probenentnahme kundenseitig)



Customer		TEST PROTOCOL						Order no.			
South Quality		(Hydrogen Induced Cracking Test - HIC)						SQO-M4 R 17			
Plate - no. ^a		Material ^a			Heat - no. ^a			Dimensions [mm] ^a			
		Steel									
Tube - no. ^a		Specimen - no. ^a		Specimen size [mm] ^b			Work-no.				
LM3528		78		Width	Thickness	Length	EDWK2025-048				
				18,0	9,2	100,8					
Specification		NACE Standard TM0284-2016									
	Specimen location	Specimen 1	x	Longitudinal specimen	Specimen 1	x	Transverse specimen	Specimen 1			
		Specimen 2			Specimen 2			Specimen 2			
		Specimen 3			Specimen 3			Specimen 3			
		Specimen 4			Specimen 4			Specimen 4			
O2 concentration											
Purge gas		Nitrogen 5.0									
Test solution		NACE Standard TM0284-2016 test solution B									
Test conditions		Temperature 25 °C			Test period 96 h						
		before H ₂ S	Test start	Day 1	Day 2	Day 3	Test end				
pH		8,2	5,1				5,2				
H ₂ S concentration (ppm)			2827				2793				
Subsection A			Subsection B			Subsection C					
L [mm]	W [mm]	A [mm ²]	L [mm]	W [mm]	A [mm ²]	L [mm]	W [mm]	A [mm ²]			
CLR %	CTR %	CSR %	CLR %	CTR %	CSR %	CLR %	CTR %	CSR %			
0,00	0,00	0,00	0,00	0,00	0,00	0,00	0,00	0,00			
average over 3 subsections			CLR =	0,00 %							
			CTR =	0,00 %							
			CSR =	0,00 %							
Corrosion laboratory		Metallography		Inspector							
Received on	27.06.2025										
Completed on	01.07.2025	14.07.2025									
Operator	Boenke	Förster									
Signature											
Approved on	14.07.2025										
Name	Dr. Haase										
Signature											


Test results only refer to the pieces tested. No part of this protocol may be reproduced without prior written permission of SZMF.
 Salzgitter Mannesmann Forschung GmbH, Standort Duisburg - Ehinger Straße 200, 47259 Duisburg - Phone: 0203 / 999 - 02

^aCustomer information (Kunden-/Auftraggeberinformationen)

Page 2 of 3

^bSampling by customer (Probenentnahme kundenseitig)



Customer		TEST PROTOCOL						Order no.		
South Quality		(Hydrogen Induced Cracking Test - HIC)						SQO-M4 R17		
Plate - no. ^a		Material ^a			Heat - no. ^a			Dimensions [mm] ^a		
		Steel								
Tube - no. ^a		Specimen - no. ^a		Specimen size [mm] ^b			Work-no.			
LM3528		134		Width	Thickness	Length	EDWK2025-047			
				18,0	8,8	100,2				
Specification		NACE Standard TM0284-2016								
	Specimen location	Specimen 1	x	Longitudinal specimen	Specimen 1	x	Transverse specimen	Specimen 1		
		Specimen 2			Specimen 2			Specimen 2		
		Specimen 3			Specimen 3			Specimen 3		
		Specimen 4			Specimen 4			Specimen 4		
		Specimen 4			Specimen 4			Specimen 4		
O2 concentration										
Purge gas		Nitrogen 5.0								
Test solution		NACE Standard TM0284-2016 test solution B								
Test conditions		Temperature 25 °C			Test period 96 h					
		before H ₂ S	Test start	Day 1	Day 2	Day 3	Test end			
pH		8,2		5,1				5,2		
H ₂ S concentration (ppm)				2827				2793		
Subsection A			Subsection B			Subsection C				
L [mm]	W [mm]	A [mm ²]	L [mm]	W [mm]	A [mm ²]	L [mm]	W [mm]	A [mm ²]		
CLR %	CTR %	CSR %	CLR %	CTR %	CSR %	CLR %	CTR %	CSR %		
0,00	0,00	0,00	0,00	0,00	0,00	0,00	0,00	0,00		
average over 3 subsections		CLR = 0,00 %		CTR = 0,00 %		CSR = 0,00 %				
		Corrosion laboratory		Metallography		Inspector				
Received on		27.06.2025								
Completed on		01.07.2025		14.07.2025						
Operator		Boenke		Förster						
Signature										
Approved on		14.07.2025								
Name		Dr. Haase								
Signature										

Test results only refer to the pieces tested. No part of this protocol may be reproduced without prior written permission of SZMF.
 Salzgitter Mannesmann Forschung GmbH, Standort Duisburg - Ehinger Straße 200, 47259 Duisburg - Phone: 0203 / 999 - 02

^aCustomer information (Kunden-/Auftraggeberinformationen)

^bSampling by customer (Probenentnahme kundenseitig)

APPENDIX B

VOID

----- END OF REPORT -----